


Technical Data Sheet

StoCalce Activ MP

Ecological, mineral finishing render as a free-style textured render on a lime base in accordance with EN 998-1



Characteristics

- Area of application**
- interior
 - modified finishing plaster in accordance with EN 998-1
 - highly suitable for Sto internal insulation systems
 - as a finishing plaster for the StoCalce Functio sorption system

Properties

- mineral
- preservative-free
- perfectly matched to the StoCalce Functio Sorption System
- highly diffusion-open
- very good moisture management
- contributes towards optimising the ambient climate
- simple and supple application
- best regulation of humidity
- rapid sorption and desorption
- MBV practical > 2.0 (g/m² * % RH) in the system with StoLevell Calce RP, StoLevell Calce FS

Appearance

- as free-style textured render

Technical data

Criterion	Standard / test specification	Value/ Unit	Notes
Minimum layer thickness		2 mm	
Maximum layer thickness		5 mm	
Mortar class	EN 998-1	CS II	
Bulk density of hardened mortar	EN 1015-10	1.3 g/cm ³	
Flexural strength (28 days)	EN 1015-11	1.3 N/mm ²	
Compressive strength (28 days)	EN 1015-11	3.7 N/mm ²	
Dynamic modulus of elasticity (28 days)	TP BE-PCC	2,900 N/mm ²	

Technical Data Sheet

StoCalce Activ MP

Water vapour diffusion-equivalent air layer thickness μ	DIN EN 1015-19	7	≤ 20
Water absorption (class)	EN 1015-18		$W_c 0$
Thermal conductivity	EN 1745	$\leq 0,45 \text{ W}/(\text{m}^*\text{K})$ für P=50%	Table value
Thermal conductivity	EN 1745	$\leq 0,49 \text{ W}/(\text{m}^*\text{K})$ für P=90%	Table value
Reaction to fire (class)	EN 13501-1	A1	
Spreading rate		830 L/t	
Capillary absorption		$> 0.4 \text{ kgm}^2\text{m}$	$W_c 0$
Bond strength on concrete	DIN EN 1015-12	$\geq 0.08 \text{ N}/\text{mm}^2$	/ fracture pattern B

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

Substrate

Requirements

The substrate must be firm, dry, clean, load-bearing, and free from sinter layers, efflorescence and release agents.

Preparations

The preparation of the substrate and the execution of the coating work must correspond to the generally recognised technological norms. All coatings and preliminary work should always be geared towards the project and the requirements it is exposed to.

Remove loose paint remnants, as well as non-load bearing existing paint coats and coatings, and clean the surface (mechanically or using a suitable paint remover).

Prime coatings must not form a glossy layer.

Normal absorbent substrates:

Prime with StoPrim Plex or StoPrim GT.

StoPrim Plex is ready-to-use and is dilutable with up to max. 30 % water.

Weakly absorbent substrates:

Prime with StoPrim Color or StoPrim Sil Color.

Water-soluble ingredients:

Isolate with StoPrep QS.

StoPrep QS is ready-to-use and should not be diluted. Stir the material well before application. The product contains a cationic binding agent and should not be mixed with other products!

Intact, two-component coatings, non-ferrous metals, plastics:

Prime with StoAqua EP Active.

Technical Data Sheet

StoCalce Activ MP

Mould-infested areas:

Treat the surfaces with Geiger STOP or coat with a 10 % hydrogen peroxide solution followed by thorough and subsequent washing with clear water. Please observe the respective national recommendations and directives when carrying out mould remediation.

When coating acrylic joint filling compounds and sealants, cracks and/or discolouration in the paint coat can occur due to the higher elasticity of the acrylic waterproofing compound. Due to the wide range of products on the market, perform your own tests to assess the adhesion.

The coating layer build-ups and recommendations listed do not release the applicator from his or her own responsibility for substrate testing and assessment.

Application

Application temperature

Lowest temperature of substrate/air: +5 °C
highest temperature of substrate and air: +30 °C

Time for application

At +20 °C: approx. 2 hours

Mixing ratio

9.5 l of water per 25 kg

Material preparation

Decant water first and add the pre-blended dry mortar. Stir for approx. 2 minutes, allow to mature for approx. 5 minutes, and then stir again for approx. 30 seconds.

Consumption

Type of application

Approx. consumption

depending on the layer thickness required

1.70 - 4.00 kg/m²

Material consumption depends on the application, substrate, and consistency, among other factors. The stated consumption values are only to be used as a guide. If required, determine precise consumption values on the basis of the specific project.

Coating build-up

Substrate coating in a new building:

StoLevell Calce RP

Single layer thickness: approx. 10 - 20 mm

Plaster substrates (e.g. gypsum plasterboard): prime with StoPrep In.

Apply StoLevell Calce FS as a bonding agent using a adhesive comb (8 x 8 mm) on non-absorbent substrates, for example concrete and XPS.

In case of heterogeneous blockwork and XPS boards: reinforce StoLevell Calce RP with Sto-Glass Fibre Mesh F (4 x 4 mm).

Substrate coating for renovation:

existing load-bearing and existing matt coatings can be directly coated with StoLevell Calce FS

Technical Data Sheet

StoCalce Activ MP

Layer thickness: 3 - 5 mm as single layer, max. 8 mm with multi-layer application

Intermediate coat:

StoLevell Calce FS

Layer thickness: 3 - 5 mm as single layer, max. 8 mm with multi-layer application

Depending on the substrate, a reinforcement with Sto-Glass Fibre Mesh F (4 x 4 mm) may be required.

Finish:

StoCalce Activ MP

Note:

If necessary, the product can be coated with StoColor Calcetura or StoColor Sil In without significantly impairing the sorption behaviour.

Application

manually

Use a rust-free steel trowel to apply the product evenly.

layer thickness of min. 2 mm and max. 5 mm in individual cases.

Application method, tool, and substrate have a significant impact on the result. The tools mentioned are recommendations only.

Drying, curing, ready for next coat

Drying time depends on the temperature, wind and relative humidity.

Cleaning the tools

Clean tools with water immediately after use.

Notes, recommendations, special information, miscellaneous

In cold and damp weather all hydraulic renders can be affected by efflorescence. This does not constitute a technical/functional defect and is no cause for a claim.

Delivery

Colour shade

natural white

can be tinted with StoLook Punto to max. 20 %

To tint the material, mix the entire content of the bag with StoLook Punto F.

Colour accuracy:

Due to the chemical and physical setting processes at different project conditions, it is not possible to give any warranty for uniform colour accuracy and freedom from stains especially with regard to:

- a) uneven absorption of the substrate
- b) different substrate moisture levels
- c) partially very different alkalinity/substances in the substrate.

Technical Data Sheet

StoCalce Activ MP

Storage

Storage conditions	Store in dry conditions.
Storage life	The quality of the product in its original container is guaranteed until the maximum storage life has expired. The storage life information is included in the batch number on the container. Explanation of batch no.: digit 1 = last digit of the year, digits 2 + 3 = calendar week Example: 1450013223 - storage life ends week 45in 2021

Identification

Product group	Internal plaster
----------------------	------------------

Composition

white Portland cement
hydrated lime
polymer powder
mineral extenders
thickener

Safety

This product is subject to compulsory labelling in accordance with the current EU regulation.
Observe the Safety Data Sheet!
Safety instructions refer to the ready-to-use, unapplied product.

Causes skin irritation.Causes serious eye damage.May cause respiratory irritation. Keep out of reach of children. Avoid breathing dust. Use only outdoors or in a well-ventilated area. Wear protective gloves/ protective clothing/ eye protection/ face protection. IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.Get immediate medical advice/ attention.IF ON SKIN: Wash with plenty of soap and water.If skin irritation occurs: Get medical advice/ attention.Take off contaminated clothing and wash it before reuse.IF INHALED: Remove person to fresh air and keep comfortable for breathing.

Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.
Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

Technical Data Sheet

StoCalce Activ MP

Sto SE & Co. KGaA
Ehrenbachstr. 1
79780 Stühlingen / Germany
Phone: +49 7744 57-0
Fax: +49 7744 57-2178
Infoservice.export@sto.com
www.sto.com